



MMG Canada Limited

## F82BX / FT82BX

- Material Type:** Manganese-Zinc Ferrite
- Properties:** High curie temperature High saturation flux density  
Good performance with frequency  
Good performance under DC Bias
- Frequency Range:** DC to 1 MHz (subject to application)
- Typical Application:** Wideband and pulse transformers, filters and common mode chokes
- Standard Geometries:** Toroids, baluns, E, RM and pot cores  
Additional shapes are available upon request



Parameter	Symbol	Standard Test Conditions			Unit	Value
Initial Permeability (nominal)	$\mu_i$	$B < 0.1 \text{ mT}$	$f = 10 \text{ kHz}$	$T = 25^\circ\text{C}$	-	5000
Saturation Flux Density (typical)	$B_s$	$H = 796 \text{ A/m (10 Oe)}$		$T = 25^\circ\text{C}$	mT	470
Remanent Flux Density (typical)	$B_r$	$H \sim 0 \text{ A/m (from near saturation)}$ $f = 10 \text{ kHz}$		$T = 25^\circ\text{C}$	mT	110
Coercivity (typical)	$H_c$	$B \sim 0 \text{ mT (from near saturation)}$ $f = 10 \text{ kHz}$		$T = 25^\circ\text{C}$	A/m	2.0
Loss Factor (maximum)	$\frac{\tan \delta}{\mu_i}$	$B < 0.1 \text{ mT}$	$f = 100 \text{ kHz}$	$T = 25^\circ\text{C}$	$10^{-6}$	< 13
Curie Temperature (minimum)	$T_c$	$B < 0.1 \text{ mT}$	$f = 10 \text{ kHz}$		$^\circ\text{C}$	200
Resistivity (typical)	$\rho$	$E = 1 \text{ V/cm}$		$T = 25^\circ\text{C}$	$\Omega \cdot \text{cm}$	100

\* Data was derived from measurements made on a standard test toroid core with an outside diameter of 30 mm





MMG Canada Limited

# F82BX / FT82BX

